

INSULATION

Pipe Insulation (6' Lengths)



Pre-Slit & Pre-Glued

Max Temp 210F°(99°C)

Flexible to -100°F (-73°C)

Wall Thickness (\$/ft)


ID Size	1/2" R		3/4" R		Pipe Size IPS - Copper
5/8"	\$.52	<u>3.5</u>	.81	<u>5.6</u>	* - 1/2
7/8"	.58	<u>3.3</u>	1.01	<u>5.1</u>	1/2 - 3/4
1 1/8"	.67	<u>3.1</u>	1.29	<u>4.8</u>	3/4 - 1
1 3/8"	.83	<u>3.2</u>	1.53	<u>4.9</u>	1 - 1 1/4
1 5/8"	1.01	<u>2.9</u>	2.16	<u>4.5</u>	1 1/4 - 1 1/2
2"	1.14	<u>2.6</u>	2.43	<u>4.1</u>	1 1/2 - *
2 1/8"	1.34	<u>2.9</u>	2.77	<u>4.3</u>	* - 2
2 3/8"	1.44	<u>2.6</u>	3.07	<u>4.0</u>	2 - *
2 5/8"	1.70	<u>2.8</u>	3.51	<u>4.2</u>	2 1/2 - *

PHYSICAL PROPERTIES


Physical Properties	Testing Parameters	Imcolock Insulation	Test Methods
Thermal Conductivity (K)	90°F (32°C) Mean Temp	.255 (.037)	ASTM C 177/C 518
	75°F (24°C) Mean Temp	.250 (.036)	ASTM C 177/C 518
BTU -in/hr - Ft ² - °F (W/mK)	50°F (10°C) Mean Temp	.245 (.035)	ASTM C 177/C 518
	Operating Temperature Range		
Flexible to -100°F (-73°C)	Upper Range	210°F (99°C)	
	Lower Range	-330°F (-201°C)	
Water Vapor Permeability Dry Cup. Perm-In		0.0	ASTM E 96
Ozone Resistance		Pass	ASTM D 1171
Chemical/ Solvent Resistance		Good	
Mildew Resistance/Air Erosion		Pass	UL 181

CFC/HCFC Free - Non-porous - Low VOCs - Halogen Free - Fiber Free

- Resistant to Mold Growth - Made with up to 100% recycled content • Made in USA



FLEX-WRAP Closed cell polyethylene pipe wrap	3/32" x 6" x 200'	\$ 21.95
COVER KIT P-trap & Angle Stops/Risers	#396	60.50
FIBERGLASS DUCT WRAP	1 1/4" x 9" x 150'	49.95
HANDI-CAP-WRAP *	1/8" x 2" x 50'	13.50



* Pressure sensitive adhesive backing

-W, 6+ -X